

Basic Light 2000 *Lightweight Self-Levelling Compound*

Product description

BL 2000 is a lightweight cement based, plastic reinforced, self levelling, and pumpable compound. Can be used in all types of dry accommodation areas before laying of carpet, vinyl, etc.

Surface preparation

BL 2000 floor levelling must be applied on hard foundations such as concrete or steel, which should be free of dust, grease, oil, dirt, etc. Anti-corrosion treated steel layer, aluminum and zinc to be pre-treated with Shop primer. When surfaces have been treated with a two-component epoxy-iron oxide primer, the DMS primer 54 can be used.

Primer

DMS primer 54 must be used on steel, concrete and between layers.

Mixing


Mix one bag of BL 2000 (18 kg) with a maximum of 7,4-7,5 litres of clean cold water and stir vigorously to a smooth, easy flowing mortar.

Application

BL 2000 floor levelling must be applied in a thickness of max. 30 mm. Depending on the working conditions, trowel or spike roller can be used. After application of BL 2000 the compound must be protected against strong, direct heat and sunlight and draught must be avoided. BL 2000 should not be exposed to freezing temperatures (Recommended curing temperature is min. 5°C).

Curing / dehydration

At +20°C and 65 % relative humidity the compound will cure after 24-36 hours, curing times depend on the thickness of the applied layer, relative humidity and ventilation at the working area. The compound must be fully dry before covering (the moisture has to be < 5 % by weight).



Basic Light 2000 *Lightweight Self-Levelling Compound*

Technical description

Basis	Cement and synthetic polymer
Colour	Grey
Density	Approx. 0,9 kg/mm/m ² (applied)
Thickness	1 - 30 mm (per layer)
Mixing ratio	Approx. 41% water
Pot life	Approx. 30 minutes at 20°C and 65 % RH
Curing time	Setting time for walking, 3-4 hours. Ready for covering after 24-36 hours at 20°C in a maximum of 10 mm thickness
Flow ability after SS 923519	130 mm
Recommended application temperature	Between +5°C and +35°C
Bending tear strength EN 13892-2	5,7 MPa
Compression strength EN 13892-2	18,4 MPa

Packaging

- 18 kg bags (50 bags per pallet)

Cleaning

Use water to clean the tools before the compound is cured.

Shelf-life

The shelf-life is min. 12 months in unopened packaging.

Storage

In dry conditions, do not expose to moisture and freezing temperature.

The information and in particular, the recommendations relating to the application and end use of DMS products, are given in good faith based on our current knowledge and experience. The information and recommendations are given without warranty of any kind and does not lead to any further liability for DMS, besides what is stated in the sales agreement. It is the buyer or end-user's responsibility to investigate or in other way make sure that DMS product suitable for the intended use and further are stored, handled and applied in accordance with stated directions. All orders are delivered and accepted in accordance with our general conditions of sale

For additional technical information, please contact our technical department.